



Const. 7x19 M
Min. & Max. Dia 8 mm - 60 mm
Core WSC
Coating UNGALVANIZED & GALVANIZED
Other Request Contact US



Rope Dia. (mm)	Dia. Tolerance (%)	Unit Weight (kg/m)	Minimum Breaking Load (kN) [Acc to Wire Tensile Strength]		
			1770 [N/mm2]	1960 [N/mm2]	2160 [N/mm2]
8	+5 0	0.244	41	45	50
9		0.309	52	57	63
10		0.381	64	71	78
11		0.461	78	86	95
12		0.549	92	102	113
13		0.644	108	120	132
14		0.747	126	139	153
15		0.858	144	160	176
16		0.976	164	182	200
17		1.101	185	205	226
18		1.235	208	230	253
19		1.376	231	256	282
20		1.524	256	284	313
21		1.681	283	313	345
22		1.845	310	343	378
24		2.195	369	409	450
26		2.576	433	480	529
28		2.988	502	556	613
32		3.903	656	727	801
36		4.939	830	920	1013
38		5.503	925	1025	1129
40		6.098	1025	1135	1251
44		7.378	1240	1374	1514
48		8.781	1476	1635	1802
52		10.305	1733	1919	2114
56		11.952	2009	2225	2452
60		13.720	2307	2554	2815

Const.
Min. & Max. Dia
Core
Coating
Other Request

6x19 M
8 mm - 60 mm
FC & IWRC
UNGALVANIZED & GALVANIZED
Contact US



Rope Dia. (mm)	Dia. Tolerance (%)	Unit Weight (kg/m)	Minimum Breaking Load (kN) [Acc to Wire Tensile Strength]			Rope Dia. (mm)	Dia. Tolerance (%)	Unit Weight (kg/m)	Minimum Breaking Load (kN) [Acc to Wire Tensile Strength]		
			1770 [N/mm2]	1960 [N/mm2]	2160 [N/mm2]				1770 [N/mm2]	1960 [N/mm2]	2160 [N/mm2]
8	+5 0	0.221	35	39	42	8	+5 0	0.244	38	42	46
9		0.280	44	49	54	9		0.309	48	53	58
10		0.346	54	60	66	10		0.381	59	65	72
11		0.418	66	73	80	11		0.461	71	79	87
12		0.498	78	87	95	12		0.549	85	94	103
13		0.584	92	102	112	13		0.644	99	110	121
14		0.677	107	118	130	14		0.747	115	128	141
15		0.778	122	135	149	15		0.858	132	146	161
16		0.885	139	154	170	16		0.976	150	167	184
17		0.999	157	174	192	17		1.101	170	188	207
18		1.120	176	195	215	18		1.235	190	211	232
19		1.247	196	217	239	19		1.376	212	235	259
20		1.382	217	241	265	20		1.524	235	260	287
21		1.524	240	265	292	21		1.681	259	287	316
22		1.672	263	291	321	22		1.845	284	315	347
24		1.990	313	347	382	24		2.195	338	375	413
26		2.336	367	407	448	26		2.576	397	440	485
28		2.709	426	472	520	28		2.988	461	510	562
32		3.538	556	616	679	32		3.903	602	666	734
36		4.478	704	780	859	36		4.939	762	843	929
38		4.990	785	869	958	38		5.503	849	940	1036
40		5.529	869	963	1061	40		6.098	940	1041	1147
44		6.690	1052	1165	1284	44		7.378	1138	1260	1388
48		7.962	1252	1386	1528	48		8.781	1354	1499	1652
52		9.344	1469	1627	1793	52		10.305	1589	1760	1939
56		10.837	1704	1887	2080	56		11.952	1843	2041	2249
60		12.440	1956	2166	2387	60		13.720	2116	2343	2582