


Const.	24x7
Min. & Max. Dia	8 mm - 52 mm
Core	FC & IWRC
Coating	UNGALVANIZED & GALVANIZED
Other Request	Contact US



Rope Dia. (mm)	Dia. Tolerance (%)	Unit Weight (kg/m)	Minimum Breaking Load (kN) [Acc to Wire Tensile Strength]		
			1770 [N/mm2]	1960 [N/mm2]	2160 [N/mm2]
8	+5 0	0.273	41	45	50
9		0.346	52	57	63
10		0.427	64	71	78
11		0.517	77	86	94
12		0.615	92	102	112
13		0.722	108	120	132
14		0.837	125	139	153
16		1.093	164	181	200
18		1.383	207	230	253
20		1.708	256	283	312
22		2.067	310	343	378
24		2.460	368	408	450
26		2.887	432	479	528
28		3.348	502	555	612
30		3.843	576	638	703
32		4.372	655	725	799
34		4.936	739	819	902
36		5.534	829	918	1012
38		6.166	924	1023	1127